Technical Data Sheet



PES 105 Aqua Putty Stick

PES 105 Aqua Putty Stick is a two component repair material in stick form which cures underwater after mixing. It is a metal repair adhesive which develops high mechanical strength in a short period of time.

Typical Applications

Suitable for emergency repairs to leaking pipe work, tank seams, and flanges.

Surface Preparation

The material is suitable for application to manually prepared surfaces, all loose material such as old coatings and repair materials must be cleaned from the surface prior to application.

Mixing and Application

The product is supplied in stick form and therefore the base and activator component are premeasured. Simply break off the required amount of material from the stick and using gloved hands knead the product until the green and cream components become a consistent light green. The product once fully mixed has a usable life of 15 mins at 68°F.

Once a consistent mix has been achieved apply the material by pressing the putty onto the prepared surface.

Cure Times

At 68°F the applied materials should be allowed to harden for the times indicated below before being subjected to the conditions indicated. These times will be extended at lower temperatures and reduced at higher temperatures:

Usable Life	15 mins
Hard Dry	45 mins
Machiningandlightloading	45 mins
Fullloading	90 mins
Immersion	90 mins

Over-coating times

Minimum - the applied material can be over-coated as soon as it is touch dry.

Maximum - the over-coating time should not exceed 3 hours.

Where the maximum over-coating time has been exceeded the surface should be abraded and cleaned.

Storage Life

5 years if unopened and store in normal dry conditions (59-86°F)

POLYMERIC ENGINEERED SOLUTIONS, 5401 HWY 21 W, BRYAN, TX 77803 PH: 979-779-8700 www.pes-solutions.com pes1@pes-solutions.com

Technical Data Sheet



Technical data and Performance

Compressive Strength	6350psi
ASTM D695	446kg/ cm²
Tensile Shear Adhesion	70kg/ cm²
ASTM D1002	1000psi
Flexural Strength	510kg/ cm²
ASTM D790	7275psi
Hardness Rockwell R ASTM D785	85
Corrosion Resistance (ASTM B117)	5000 hours

Health and Safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read the fully detailed Material Safety Data Sheet.

Legal Notice: The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. PES accepts no liability arising out of the use of this information or the product described herein.